

(19) World Intellectual Property Organization
International Bureau




(43) International Publication Date
2 November 2000 (02.11.2000)

PCT

(10) International Publication Number
WO 00/65700 A3

- (51) International Patent Classification⁷: H01S 5/40, 5/183, H01L 31/0232, 33/00
- (21) International Application Number: PCT/US00/11048
- (22) International Filing Date: 25 April 2000 (25.04.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/300.253 27 April 1999 (27.04.1999) US
- (71) Applicant: GORE ENTERPRISE HOLDINGS, INC.
[US/US]: 551 Paper Mill Road, P.O. Box 9206, Newark, DE 19714 (US).
- (72) Inventors: COLDREN, Larry; 4665 Via Vistosa, Santa Barbara, CA 93110 (US). AKULOVA, Yuliya; 425 Benner Road, Apt. 201, Allentown, PA 18104 (US). FIORE, Andrea; Via Marco Atilio, I-00136 Roma (IT).
- (54) Title: POSTGROWTH ADJUSTMENT OF CAVITY SPECTRUM FOR SEMICONDUCTOR LASERS AND DETECTORS
- (74) Agents: CAMPBELL, John, S. et al.: W. L. Gore & Associates, Inc., 551 Paper Mill Road, P.O. Box 9206, Newark, DE 19714-9206 (US).
- (81) Designated States (*national*): AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW.
- (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— With international search report.
- (88) Date of publication of the international search report:
18 January 2001
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



(57) Abstract: A method for selectively tuning the wavelength of optical cavities in semiconductor lasers and detectors after epitaxial growth using lateral wet oxidation. Tuning layers of $\text{Al}_x\text{Ga}_{1-x}\text{As}$ and $\text{Al}_y\text{Ga}_{1-y}\text{As}$ are positioned inside or adjacent to the optical cavity. Wet lateral oxidation is then used to transform the high-index semiconductor into a low-index oxide for tuning. The oxidation proceeds laterally into the $\text{Al}_x\text{Ga}_{1-x}\text{As}$ and then attacks the $\text{Al}_y\text{Ga}_{1-y}\text{As}$ layer vertically. The ratios of the oxidation rates can be controlled by adjusting the compositions of the materials, most notably because the oxidation rate increases as the amount of aluminum increases. The oxidized thickness depends on the time that the tuning layer is exposed to vertical oxidation. Due to the change in optical index from the semiconductor to the oxide, the optical thickness and the resonant wavelength of the cavity are also tailored along the lateral oxidation. As a result, the resonant wavelength of a device depends on its distance from the etched edge.

WO 00/65700 A3

BEST AVAILABLE COPY

PCT/US 00/11048

IPC 7 H01S5/40 H01S5/183 H01L31/0232 H01L33/00

Claessen, L

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/US 00/11048

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WIPIEJEWSKI T ET AL: "VERTICAL-CAVITY SURFACE-EMITTING LASER DIODES WITH POST-GROWTH WAVELENGTH ADJUSTMENT" IEEE PHOTONICS TECHNOLOGY LETTERS, US, IEEE INC. NEW YORK, vol. 7, no. 7, 1 July 1995 (1995-07-01), pages 727-729, XP000516835 ISSN: 1041-1135	6,7,9, 26,43
Y	the whole document	14
X	CHANG-HASNAIN C: "VERTICAL-CAVITY SURFACE-EMITTING LASERS: 2-D ARRAYS" PROCEEDINGS OF THE OPTICAL FIBER COMMUNICATION CONFERENCE, US, NEW YORK, IEEE, vol. CONF. 15, 2 February 1992 (1992-02-02), page 100 XP000341618 ISBN: 1-55752-222-7	6,7,9,26
Y	the whole document	3
A	FIGORE A ET AL: "LOW-THRESHOLD MULTIPLE-WAVELENGTH VERTICAL-CAVITY LASER ARRAYS OBTAINED BY POSTGROWTH WET OXIDATION" ELECTRONICS LETTERS, GB, IEE STEVENAGE, vol. 34, no. 19, 17 September 1998 (1998-09-17), pages 1857-1858, XP000853427 ISSN: 0013-5194 the whole document	1-46
X	FIGORE A ET AL: "Postgrowth tuning of cavity resonance for multiple-wavelength laser and detector arrays" TECHNICAL DIGEST. SUMMARIES OF PAPERS PRESENTED AT THE CONFERENCE ON LASERS AND ELECTRO-OPTICS. CONFERENCE EDITION. 1998 TECHNICAL DIGEST SERIES, VOL.6 (IEEE CAT. NO.98CH36178), TECHNICAL DIGEST SUMMARIES OF PAPERS PRESENTED AT THE CONFERENCE ON LASE, pages 467-468, XP002150211 1998, Washington, DC, USA, Opt. Soc. America, USA ISBN: 1-55752-339-0 the whole document	1,3,6,7, 9,26,43
A	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 09, 30 September 1997 (1997-09-30) & JP 09 135051 A (NEC CORP), 20 May 1997 (1997-05-20) abstract.	1-46

BEST AVAILABLE COPY

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/11048

Patent document cited in Search report	Publication date	Patent family member(s)	Publication date
JP 09135051 A	20-05-1997	JP 2806333 B	30-09-1998

BEST AVAILABLE COPY